

stylex




Lena

Lena


(Click [here](#) to view full 72-color palette and order memo samples)



6644
Azure



8050
Snow




8000
White




3392
Ming




3328
Camel




5478
Caramel




8023
Clay




2511
Ferrari




6622
Cardinal




5484
Salsa




3368
Chateau




2257
Java



3370
Espresso



3364
Sequoia



3324
Nutmeg




3326
Alba



1414
Café Latte




3390
Safari




3396
Linen




3394
Pietra




3388
Putty




1464
Elfin




9200
Quahog




2526
Sterling




1413
Greystone




2523
Mystic




9187
Onda




2208
Ghiaccio




3348
Tahoe




9199
Heather




2500
Pewter




443
Mariner




2583
Cobalt



9000
Black



5454
Celtic



2561
Evergreen



9188
Acqua

Lena

Full grain leather with even coloration throughout the entire hide. Superior selection of European and New Zealand cattle hides are hand selected for Lena. These hides are recognized industry wide for their clean surfaces and excellent cutting yields. Luxurious soft hand and smooth supple surface make this one of the most beautiful leathers available. The protective finish allows Lena to be suitable for most public and private environments.

REACH (EC 1907/2006) compliant production aims to improve the protection of human and environmental health. Processed using low emission mineral tanning formulas which are environmentally respectful, the hides are retanned in aged oak drums using vegetable agents, natural fat liquors, oils and dyes that ensure the leather is properly through dyed. Natural color variations may occur even within the same dye lot.

Application: Aviation*, Contract, Hospitality, Residential, Marine**

Raw Material: European and New Zealand

Hide Size: Average 48 sqft

Thickness: 0.9 to 1.0 mm

Wet Rub Test: (Nr 150): IUF 450 / UNI EN ISO 11640: ≥ 4 grey scale

Dry Rub Test: (Nr 500): IUF 450 / UNI EN ISO 11640: ≥ 4 grey scale

Abrasion: (ASTM D 3884-92) 500 gram load: 1500 cycles

Abrasion: Wyzenbeek (ASTM D4157) 100,000 Rubs

Alkaline ph 8: IUF 450 / UNI EN ISO 11640: ≥ 4 grey scale

Flexing Endurance: IUP 20: $\geq 30,000$

Tear Strength: IUP 40 / UNI EN ISO 3377-I: ≥ 20 N

Adhesion: IUF 470 / UNI EN ISO 11644: ≥ 3.50 N/cm

Water repellency: AATCC 22-2010: 93

Light resistance (Xenon Test): IUF 402 / UNI EN ISO 105-B02: 5 blue scale

Flammability Resistance: UFAC Class 1, CAL TB 117-2013, NFPA 260

Soil/Stain Release: AATCC 130-2015: Grade 5 represents best stain removal (immediate). Nail polish remover (5), Betadine (5), Bleach (5), Urine (5), Blood (5). Fluid Resistance: Red wine (5), Beer (5), Whiskey (4.5), Cola (5), Coffee (4.5), Red Bull (5) Mayonnaise (5), Olive Oil (5), Catsup (5), Vegetable oil (5), Chocolate (melted) (5), Lipstick (3.5), Lysol (5), Formula 409 (5), Windex (5). Test procedure modified to clean stains with 1 part household bleach/10 parts water solution.

Bleach Cleanable: BIFMA Health Care Furniture 8.1-2017 Section 7: Household bleach (sodium hypochlorite). CDC/EPA recommended ratios (1:48) parts bleach to water for the sanitizing and disinfecting of viruses and bacteria. Reference CDC/EPA and product specifications for approved dilution ratio and cleaning agent instructions for dwell time.

Origin: Italy

*May be treated to meet Federal Aviation Regulations for Flammability Resistance.

**May be treated to meet Wheelmark IMO Resolution A.652(1b).